

Gasket sheet AF-OIL typ 235

Application:

Oil-proof sheet, recommended for high temperatures and pressures. Approved for use in sub-inspection connections, in natural gas transfer, mining engineering, food industry and potable water transfer.



TECHNICAL PARAMETERS:

Standards satisfied and approvals	DuPont Specification G-81 UDT PZH DVGW Germanischer Lloyd
Classification per DIN 28091-2	FA-AM1-O
Basis	aramid fibres, mineral fibres, NBR caoutchouc
Density	2,0
Maximal operating conditions: Peak temperature	350°C
Continous temperature	300°C
Continous temperature in steam Pressure -	230°C 10 MPa
Factors per ASME Code: "y" "m"	1,2 1,8
Factors per DT-UC-90/WO-0/19 S_m dla 1mm,2mm,3mm S_r dla 1mm,2mm,3mm b dla 20, 200 i 300°C	40 Mpa; 21 Mpa; 12 Mpa 6,4 p _o ; 5p _o ; 4,1 p _o 1,1; 1,8; 3,0