

MATERIALS /МАТЕРИАЛОВ

Body and Bonnet materials / Материалов корпус-крышка

Material Group	Common Name	Nominal Type	UNS	Forging Spec.	Casting Spec. Equivalent	DIN	DIN W.Nº	Application Notes
Carbon Steel	CS	C-Mn-Fe	K03504	A105N	A216-WCB	C22.8 DIN 17243	1.0460	General non-corrosive service from-20F(-29C) to 800F(427C)
Low Temperature Carbon Steel	LTCS	C-Mn-Fe	K03011	A350-LF2	A352-LCA A352-LCB A352-LCC	TSTE 355 DIN 18103	1.0566	General non-corrosive service from-50F(-46C) to 650F(340C), LF2 to 800F(427C)
Low Temperature Alloy Steel	Nickel Steel	3.1/2 Ni	K32025	A350-LF3	A352-LC3	10Ni14	1.5637	-150F(-101C) to 650F(340C)
Low Alloy Steel	Moly Steel	C-1/2Mo	K12822	A182-F1	A217-WC1	15M03	1.5415	Up to 875F(468C)
	Alloy Steel Chrome Moly	1.1/4Cr-1Mo	K11572	A182-F11 cl2	A217-WC6	13CRMO44	1.7335	Up to 1100F(593C)
		2.2/4Cr-1Mo	K21590	A182-F22 CL3	A217-WC9	10CRM0910	1.7380	Up to 1100F(593C) HP steam
		5Cr-1/2Mo	K41545	A182-F5	A217-C5	12CRM0195	1.7362	Hing temp refinery service
		9Cr-1Mo	K90941	A182-F9	A217-C12	X 12 CrMo 9 1	1.7386	Hing temp erosive refinery service
		9Cr-1Mo-V		A182-F91	A217-C12A	X 10 CrMo VNb 9 1	1.4903	Hing pressure steam
Stainless Steel	Austenitic S Steel 300 series S Steel	304:18Cr-8Ni	S30400	A182-F304	A351-CF8	DIN X5CrNi 18 9	1.4301	0.04% min.carbon for temp. > 1000F(538C)
		304L:18Cr-8Ni	S30403	A182-F304L	A351-CF3	X 2 CrNi 19 11	1.4306	Up to 800F(427C)
		304H:	S30409	A182-F304H		n/a	n/a	
		316:16Cr-12Ni-2Mo	S31600	A182-F316	A351-CF8M	DIN X5CrNiMo 18 10	1.4401	0.04% min.carbon for temp. > 1000F(538C)
		316L:16Cr-12Ni-2Mo	S31603	A182-F316L	A351-CF3M	X 5 CrNiMo 17 12 2	1.4404	Up to 800F(427C)
		316H:	S31609	A182-F316H		n/a	n/a	
		316Ti:	S31635	A182-F316Ti		X 6 CrNiMoTi 17 12 2	1.4571	
		321:18Cr-10Ni-Ti	S32100	A182-F321		X 6 CrNiTi 18 10	1.4541	0.04% min carbon(grade F321H)and heat treat at 2000F(1100C)for service temps.> 1000F(538C)
		321H:	S32109	A182-F321H		n/a	n/a	
		327:18Cr-10Ni-Cb(Nb)	S34700	A182-F347	A351-CF8C	DIN 8556	1.4550	0.04% min carbon(grade F347H)and heat treat at 2000F(1100C)for service temps > 1000F(538C)
		347H	S34709	A182-F347H		n/a	n/a	
		317L	S31703	A182-F347L	A351-CG3M	X 6 CrNiMo 18-16-4	1.4438	
	Alloy 20	28Ni-19Cr-Cu-Mo	N08020	A182-F20	A351-CN7M	DIN 1.4500	2.4660	sevice to 600F(316C)
	Duplex 2205	22cr-5Ni-3Mo-N	S31803 S32205	A182-F51	A890-J92205	X2CrNiMoN22-5-3 DIN10088-1(95)	1.4462	sevice to 600F(316C)-The original S31803 UNS designation has been supplemented by S32205which has higher minimum N Cr and Mo
	Supper Duplex 2507	25cr-7Ni-4Mo-N	S32750	A182-F53	A351-CD4MCu A8905A	X1CrNiMoCuN25-7-4 DIN10088-1(95)	1.4501	sevice to 600F(316C)
	Supper Austentic 6Mo	20Cr-18Ni-6Mo	31254	A182-F44	A351-CK3MCuN	X2CrNiMoCuN20-18-7 DIN10088-1(95)	1.4547	sevice to 600F(316C)
Nickel-Iron Alloy	Incaloy 800	33Ni42Fe-21Cr	N08800	B564-N08800		X10mNiCrAlTi32-20	1.4876	sevice to 1000F(538C)
	Incaloy 825	42Ni-21.5Cr-3Mo-2.3Cu	N08825	B564-N08825	A494-Cu5CuC	DIN 17744	2.4858	sevice to 600F(316C)for N02200,1200F(648C) for N02201
Nickel	Nickel	99/95Ni	N02200	B160-No2200(bar)	A494-CZ-100	NW200	1.7740	
Nickel-Copper	Monel 400	67Ni-30Cu	N04400	B564-N04400	A494-M35-1	DIN 17730	2.4360	
	Monel 500		N05500	B564-N0500			2.4375	
Nickel-Alloy	904l		N08904	904L	n/a	Z2NCDU 25-20	1.4539	
Nickel Superalloys	Inconel 600	72Ni-15Cr-8Fe	N06600	B564-N0600	A494-CY40	DIN 17742	1.4816	
	Inconel 625	60Ni-22Cr-9Mo-3.5Cb	N06625	B564-N06625	A494-CW-6MC		2.4856	Difficult to folge in close dye
	Hastelloy C-276	54ni-15cr-16Mo	N10276	B564-N10276	A494-CW-2M	NiMo 16 Cr 15 W	2.4819	Difficult to folge in close dye
Titanium	Titanium	98Ti	R50400	B381-Gr-2	B367-C2	Ti 2	3.7035	